



210002349115



中国认可
国际互认
检测
TESTING
CNAS L1209

Test Report

Report Number: WT20240132(E)

Name of Sample: PVB film for building

Client: VFG FILM JOINT STOCK COMPANY

Test Category: Consignment inspection

China Building Material Test&Certification Group Qinhuangdao Co.,Ltd.

National Glass Quality Inspection and Testing Center



说 明

Notice

1. 本报告无“检验检测专用章”和骑缝章无效。

This test report is invalid without the seal.

2. 本报告无“编制、审核、批准”签字无效。

This report is invalid without signatures of responsible persons.

3. 本报告涂改无效、部分复制未经本机构批准无效。

This report is invalid when it is altered or partial copied without the approval of this institution.

4. 对本报告若有异议，应于收到报告之日起十五日内向本机构提出，逾期不予受理。

Any objection to this report should be handed to us within 15 days of the composition, or it would be dismissed.

5. 委托检测样品和委托信息由委托人提供，本机构不对其真实性负责，委托检测结果仅适用于收到的样品。未加盖资质认定和实验室认可印章时，检测数据仅供委托方内部使用，不对社会起证明作用。

Samples and related information for the commissioned test are provided by applicant, we do not responsible for the authenticity of them. The test report that we composed is only responsible for the samples received. When the seals of CMA and CNAS are not stamped, the test data is only for the internal use of the client and does not serve as a proof to the society.

6. 本报告检测结论是根据判定依据仅对所检项目得出，不代表未经检测的项目能符合要求。

The inspection conclusion of this report is based on the judgment basis only for the items examined, and does not mean that the untested items can meet the requirements.

7. 未经本机构书面同意，本报告及数据不得进行不当宣传。

Without the written consent of this institution, this report and data cannot be improperly promoted.

Test Report

1 of 4 pages

Name of sample	PVB film for building	Trademark	/
Client	VFG FILM JOINT STOCK COMPANY	Contact information	13242466628
Address of client	2nd Floor, Detch Building, 8 Ton That Thuyet, My Dinh 2 Ward, Nam Tu Liem District, Ha Noi, Vietnam	Test Category	Consignment inspection
Manufacture	VFG FILM JOINT STOCK COMPANY	Class/Category	Building film
Contract number	20240037	Production date/Batch number	/
Judgment method	GB/T 32020-2015	Date of accepting sample	Jan. 11, 2024
Test address	No. 91, West Section of Hebei Street, Haigang District, Qinhuangdao City, Hebei Province	Test item	Size, Volatile mass fraction, etc.
Sample information	Specification & quantity: Film 7m×1000mm 2 pieces Laminated glass 300mm×150mm 2 pieces Laminated glass 60mm×60mm 3 pieces Laminated glass 300mm×300mm 6 pieces Film thickness:0.76mm Laminated glass structure: 3mm clear glass+0.76mmPVB+3mm clear glass Model /color: Colorless Sample status: PVB samples aluminum film sealed package, meet the testing requirements		
Conclusion	Upon testing, the test items of the PVB film for building meet the requirements of the building film in GB/T 32020-2015 "Polyvinyl butyral interlayer for laminated glass". (the following blank)		
Remarks			

Editor: 梁晓雷

Auditor: 李同川

Approval: 李同川

Dedicated Inspection Seal

Date of issue: Jan. 31, 2024

检验检测专用章



Test Report Result

2 of 4 Pages

Name of sample		PVB film for building		Sample Coding		JP2024-003	
Test Item		Test method	Sample number	Test results		Criterion (GB/T 32020-2015)	Single conclusion
Size		GB/T 32020-2015 5.3	26~27	Length deviation: 14.0mm, 12.0mm Width deviation: 13.0mm, 10.0mm Thickness deviation: -0.01mm、-0.01mm Adjacent two points deviation: 0.010mm、0.008mm		Article 4.2, Article 6.4.1	Qualified
Volatile mass fraction		GB/T 32020-2015 5.4.1	23~25	Average: 0.37%		0.35%~0.55%	Qualified
Yellow index		HG/T 3862-2006	12~14	Average: 4.2		≤8	Qualified
Rough-ness Rz	Front	GB/T 32020-2015 5.4.3	26	Average: 30μm		15μm~50μm	Qual-ified
	Back			Average: 22μm			Qual-ified
Dimensional change rate		GB/T 32020-2015 5.4.4 GB/T 12027-2004	20~22	Average value of transverse dimensional change rate: 1.0% Average value of longitudinal dimensional change rate: -0.7%		≤12%	Qualified
Tensile strength		GB/T 32020-2015 5.4.5 GB/T 1040.3-2006 GB/T 1040.1-2006	15~19	Average: 26.3MPa		≥20.0MPa	Qualified
Fracture tensile strain		GB/T 32020-2015 5.4.5 GB/T 1040.3-2006 GB/T 1040.1-2006	15~19	Average: 218.9%		≥200%	Qualified
Knocking value		GB/T 32020-2015 5.4.6	1~2	Average: 9		≥8	Qualified
Light transmittance		GB/T 32020-2015 5.4.7 GB/T 2410-2008 Method A Haze meter method	3~5	Average: 89.2%		≥85%	Qualified

(Continued on next page)



Test Report Result

3 of 4 Pages

Name of sample	PVB film for building		Sample Coding	JP2024-003	
Test Item	Test method	Sample number	Test results	Criterion (GB/T 32020-2015)	Single conclusion
Haze	GB/T 32020-2015 5.4.7 GB/T 2410-2008 Method A Haze meter method	3~5	Average: 0.25%	$\leq 0.70\%$	Qualified
High temperature resistance	GB/T 32020-2015 5.4.8 GB/T 5137.3-2002 6	6~8	3 samples did not produce bubbles, discoloration and other defects beyond 15mm from the edge or 10mm from the crack	Article 4.3, Article 6.4.1	Qualified
Humidity resistance	GB/T 32020-2015 5.4.9 GB/T 5137.3-2002 7	9~11	3 samples did not produce bubbles, discoloration and other defects beyond 15mm from the edge or 10mm from the crack	Article 4.3, Article 6.4.1	Qualified
Radiation resistance	GB/T 32020-2015 5.4.10 GB/T 5137.3-2002 5	3~5	Irradiation resistance: 99.63%, 99.97%, 99.62%	$\geq 95\%$	Qualified
Remarks: /					
Blanks here					
Reporter: 梁晓雷			Checker: 张敬		
Date of test: Jan. 15, 2024 to Jan. 30, 2024					

Instruments list

4 of 4 pages

NO.	Instrument name	Instrument number
1	Steel ruler	QCTC-B-025
2	Steel tape	QCTC-B-063
3	Bench thickness gauge	QCTC-B-112
4	Blast drying oven	QCTC-A-104
5	Electronic balance	QCTC-A-231
6	Vacuum drying chamber	QCTC-A-233
7	Spectral colorimeter	QCTC-A-004
8	Roughness Tester	QCTC-A-234
9	High and low temperature test chamber	QCTC-A-058
10	Electronic all-purpose testing machine	QCTC-A-072
11	Electronic digital caliper	QCTC-B-090
12	Knock test box	QCTC-A-236
13	High precision haze meter	QCTC-A-239
14	Boiling box	QCTC-A-015
15	Constant temperature and humidity test chamber	QCTC-A-030
16	Radiation resistance detector	QCTC-A-024

本机构联系方式

Contact information

通讯地址 (Address): 中国河北省秦皇岛市河北大街西段 91 号

91st Hebei Ave west, Qinhuangdao, Hebei Province, P.R. China

邮编 (Post Code): 066004

电 话 (Tel): (86-335) 8388121 5911501

传 真 (Fax): (86-335) 8051865


网 址 (Web): <http://www.jctc.cn>

电子邮箱 (E-mail): gbzjzx@163.com

投诉电话 (complaint tel): 0335-5911503



微信



官网



